

**Smith - Emery Company**  
**Full Service Testing Laboratory, Established 1904**  
**781 East Washington Boulevard \* Los Angeles, California 90021**

---

FILE NO: 19246  
LAB. NO: T-98-109

12/12/1998

Tesco Products  
25601 West Ave Stanford  
Valencia, CA 91355

SUBJECT: 12" x 12" Terrazzo, Marble and Granite Tiles sealed  
with **Tesco Crystal Cote**

SPECIFICATION: ASTM C1028 (Modified per Ceramic Tile Institute)

SOURCE: Submitted to Laboratory by Tesco Products

STATIC COEFFICIENT OF FRICTION (ASTM C 1028 MODIFIED)

<u>TEST CONDITION</u>	<u>AREA</u>	<u>AVERAGE</u>	<u>COEFFICIENT</u>
dry leather	Terrazzo	37.25	0.75
	Marble	33.50	0.67
	Granite	33.00	0.66
dry rubber	Terrazzo	52.00	1.04
	Marble	51.50	1.03
	Granite	51.00	1.02
wet leather	Terrazzo	38.00	0.76
	Marble	34.00	0.68
	Granite	34.75	0.70
wet rubber	Terrazzo	42.00	0.84
	Marble	41.50	0.83
	Granite	41.00	0.82

REQUIREMENT: The Ceramic Tile Institute identifies tile in the following 3 categories:  
1. slip resistant 0.60 or greater  
2. conditionally slip resistant 0.50-0.60  
3. questionable less than 0.50

**Smith - Emery Company**

Donald W. Kaufmann, P.E.  
RQE#3882